

Country Oak

Size: 600X148 mm | **Design:** Modern | **Finish:** Matte Finish in Ceramic Floor Body | **Series:**



Front View



Scale View

Packaging Details

| Size | No. of tiles in box | Coverege Area | |
|------------|---------------------|---------------|-------|
| | | sq/mtr | sq/ft |
| 600X148 mm | 10.0 | 0.89 | 9.56 |

Technical Specification

| Sr.No. | Test Description | Standard Test Method | ISO 13006 : 2018 | Nitco's Value | |
|--------|--|-----------------------|-------------------------------|--------------------------------|-------------|
| | | | Specification Bia | 600 mm side | 148 mm side |
| 1 | Length and Width | ISO 10545-2 / EN 98 | ± 0.3 % (Max ± 1.0 mm) | ± 0.15% | ± 0.3% |
| 2 | Thickness | ISO 10545-2 / EN 98 | ± 5.0 % (Max ± 0.5 mm) | ± 5.0% | |
| 3 | Straightness of sides | ISO 10545-2 / EN 98 | ± 0.3 % (Max ± 0.8mm) | ± 0.13% | ± 0.3% |
| 4 | Rectangularity | ISO 10545-2 / EN 98 | ± 0.3 % (Max ± 1.5 mm) | ± 0.20% | ± 0.3% |
| 5 | Surface flatness | ISO 10545-2 / EN 98 | | | |
| | a. Centre curvature | ISO 10545-2 | ± 0.4 % (Max +1.8 mm) | ± 0.20% | |
| | b. Edge curvature | ISO 10545-2 | | ± 0.20% | ± 0.40% |
| | c. Warpage | ISO 10545 - 2 | | ± 0.20% | |
| 6 | Surface Quality | ISO 10545-2 / EN 98 | 95% free from visible defects | >95% free from visible defects | |
| 7 | Water Absorption | ISO 10545-3 / EN 99 | 3% < E 6% | < 6% | |
| 8 | Breaking Strength, N | ISO 10545-4 / EN 100 | Min 1000 N | >1000 N | |
| 9 | Modulus of Rupture (MOR), N/mm ² | ISO 10545 -4 / EN 100 | Min. 22 | >22 | |
| 10 | Abrasion Resistance (PEI III, IV, V) | ISO 10545-7 / EN 154 | As Specified by Manufacture | As Specified | |
| 11 | Thermal Shock Resistance | ISO 10545-9 / EN 104 | Resistant to 10 cycle | Resistant | |
| 12 | Crazing Resistance | ISO 10545-11 / EN 105 | No Crazing | Resistant | |
| 13 | Resistance to Acids, Alkalies and Chemicals (Except HF Acid) | ISO 10545-13 / EN 106 | No Visible effect | No Visible effect | |

WANT TO GET IN TOUCH WITH US?

Toll Free: 1800 266 4826 | Email: marketing@nitco.in