




## Strips Antique

**Size:** 600X600 mm | **Design:** Wood | **Finish:** Matte Finish in Ceramic Floor Body | **Series:** Ceramix Digital



Front View



Scale View

### Packaging Details

| Size       | No. of tiles in box | Coverege Area |       |
|------------|---------------------|---------------|-------|
|            |                     | sq/mtr        | sq/ft |
| 600X600 mm | 4.0                 | 1.44          | 15.5  |

### Technical Specification

| Sr.No.                                      | Test Description      | Standard Test Method             |                                     | Nitco's Value |
|---|-----------------------|----------------------------------|-------------------------------------|---------------|
|   |                       | 1                                | ISO13006:2018<br>Specification BIIa |               |
| Length and Width                            | ISO 10545-2 / EN 98   | $\pm 0.3\%$ ( Max $\pm 1.0$ mm ) | $\pm 0.15\%$                        | 2             |
| Thickness                                   | ISO 10545-2 / EN 98   | $\pm 5.0\%$ ( Max $\pm 0.5$ mm ) | $\pm 5.0\%$                         | 3             |
| Straightness of sides (%)                   | ISO 10545-2 / EN 98   | $\pm 0.3\%$ ( Max $\pm 0.8$ mm ) | $\pm 0.13\%$                        | 4             |
| Rectangularity                              | ISO 10545-2 / EN 98   | $\pm 0.3\%$ ( Max $\pm 1.5$ mm ) | $\pm 0.15\%$                        | 5             |
| Surface Flatness                            | ISO 10545-2 / EN 98   | $\pm 0.4\%$ ( max +1.8 mm )      | $\pm 0.30\%$                        | 6             |
| Surface Quality                             | ISO 10545-2 / EN 98   | 95% free from visible defects    | >95% free from visible defects      | 7             |
| Water Absorption                            | ISO 10545-3 / EN 99   | 3% < E 6%                        | 3-6%                                | 8             |
| Breaking Strength, N                        | ISO 10545-4 / EN 100  | Min 1000 N                       | >1100 N                             | 9             |
| Modulus of Rupture (MOR), N/mm <sup>2</sup> | ISO 10545-4 / EN 100  | Min. 22                          | >22                                 | 10            |
| Abrasion Resistance (PEI III, IV, V)        | ISO 10545-7 / EN 154  | As Specified by Manufacture      | As Specified                        | 11            |
| Thermal Shock Resistance                    | ISO 10545-9 / EN 104  | Resistant to 10 cycle            | Resistant                           | 12            |
| Crazing Resistance                          | ISO 10545-11 / EN 105 | No Crazing                       | Resistant                           | 13            |

---

WANT TO GET IN TOUCH WITH US?

Toll Free: 1800 266 4826 | Email: [marketing@nitco.in](mailto:marketing@nitco.in)