


NITCO



Brillo Ivory Gold

Size: 600 X 600 mm | **Design:** Natural | **Finish:** Glossy Finish in Vitrified SST Body | **Series:** Soluble Salt



Front View



Scale View

Packaging Details

| Size | No. of tiles in box | Coverage Area | | Thickness |
|--------------|---------------------|---------------|-------|-----------|
| | | sq/mtr | sq/ft | |
| 600 X 600 mm | 4.00 | 1.44 | 15.50 | |

Technical Specification

| Sr.No. | Properties | CEN Code | ISO CODE ISO13006:2012E | Requirement for Vitrified Tiles as per Bla Group | NITCO VALUE |
|--------|---------------------------------------|----------|----------------------------|--|--|
| 1 | Deviation in Length % | EN 98 | ISO 10545 - 2 | ±177 0.6 % (Max ±177 2.0 mm) | ±177 0.1 |
| 2 | Deviation in Thickness % | EN 98 | ISO 10545 - 2 | ±77 5.0 % (Max ±177 0.5 mm) | ±177 5.0 |
| 3 | Straightness of Edge % | EN 98 | ISO 10545 - 2 | ±177 0.5 % (Max ±177 1.5 mm) | ±177 0.2 |
| 4 | Diagonal Variation % (Rectangularity) | EN 98 | ISO 10545 - 2 | ±177 0.5 % (Max ±177 2.0 mm) | ±177 0.2 |
| 5 | Surface Flatness % | EN 98 | ISO 10545 - 2 | ±177 0.5 % (Max ±177 2.0 mm) | ±177 0.2 |
| 6 | Surface Quality | EN 98 | ISO 10545 - 2 | min 95 % free from any Visible Defects | min 95 % free from any Visible Defects |
| 7 | Water Absorption % By WT | EN 99 | ISO 10545 - 3 | < 0.5 | < 0.07 |
| 8 | Modulus of Rupture N/mm ² | EN 100 | ISO 10545 - 4 | > 35 | > 40 |
| 9 | Thermal Shock Resistance | EN 104 | ISO 10545 - 9 | No Visible Defects | Resistant |
| 10 | Chemical Resistance (Except HF Acid) | EN 106 | ISO 10545 - 13 | No Visible Effect | No Visible Effect |
| 11 | Resistance To Stain | | ISO 10545 - 14 | Test Method available | Class 3 |
| 12 | Deep Abrasion Resistance | | ISO 10545 - 6 | Max 175 CUBIC MM | Max 175 CUBIC MM |
| 13 | Gloss Value | | | MIN 75 For platinum and > 50 for Diamond | > 80 For platinum and > 55 for Diamond |

WANT TO GET IN TOUCH WITH US?

Toll Free: 1800 266 4826 | Email: marketing@nitco.in